




Product name		Product group	Production location
Cambridge Gault		B2	Beek
A mix of different kinds of clay - "Brunsummer"and "Maas" - forms the basis for this facing brick. By using specific sand types for surface covering, the desired colour is achieved.			
Colour			
Unicoloured ivory white			
Format			
Moulding method		Hand form	
DF: 216 x 100 x 66 mm		Between batches the average size and color may slightly differ.	
Essential Characteristics - EN771-1			
			EN 771 - 0620-CPR-53104
Dimensional tolerances	T2		
Range	R1		
Active Soluble Salts	S2		
Mean Compressive strength	>= 25 N/mm ²	Tested to the bed face	
Normalized Compressive strength	>= 20 N/mm ²	Tested to the bed face	
Dimensional stability	NPD		
Bond Strength general	0,15 N/mm ²		
Bond Strength thin layer	0,30 N/mm ²		
Reaction to fire	A1	Category	
Water absorption	<= 10% m/md		
Water vapour permeability	50/100		
Net dry density	1900 kg/m ³ (D1)		
Gross dry density	1750 kg/m ³ (D1)		
Thermal conductivity Lambda 50/50	<=0,53 W/m.K		
Durability against freeze thaw	F2		
Dangerous substances	NL-BSB	According to Annex ZA 3	
Other Characteristics			
Initial rate of water absorption - Non-coated Bricks	0,5 - 1,5 kg/m ² .min (IW2)	Value according EN771-1:2011 - 5.3.8	
Initial rate of water absorption - Coated bricks	NPD	Value according EN771-1:2011 - 5.3.8	
Freeze/thaw resistance	NPD	B 27-009	
Thermal conductivity Lambda 90/90	NPD		
Thermal conductivity Lambda Ui	NPD		
Thermal conductivity Lambda Ue	NPD		
<div></div>			
Storage & handling		Cutting	
<div>- Store packs on a clean surface and cover them - Process from multiple packs at the same time - Follow the Vandersanden processing guidelines</div>		Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).	
*All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a “C” logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.			