

Product Data Sheet



Westfield Yorkstone



Description

Appearance	Hard, fine grained sandstone.
Finishes	Sawn or sandblasted.
Governing Standards	Where applicable BS EN 1341/1342/1343 will be applied.
Quarry of Origin	Bradford, West Yorkshire.

Physical Properties

Work Dimensions	To customers' specification
Tolerances on Dimensions	Class 2
Compressive Strength	112 MPa
Flexural Strength	13.1 MPa
Material Density	2437kg/m ³ (typically)
Slip Resistance	74 Wet – D. Sawn Finish 81 Dry – D. Sawn Finish
Water Absorption	2.4%
Abrasion Resistance	18mm

Supply

Crate Size	Maximum 1.8 tonnes. Approx. size 1.0 x 1.0 x 0.80 high
Packaging	Wooden crates, suitable for stacking and transportation by fork lift.

Cleaning and Maintenance

All stones vary and each one should be looked at on an individual basis. Many are slightly alkali so acid cleaners should be avoided. A small, inconspicuous area should always be tested first. Mechanical cleaning equipment should be purpose designed to sweep a particular area. If there is any doubt about suitability, the vehicle manufacturer should be consulted. For more information regarding cleaning and maintenance, please contact our technical department.



BBS Brick & Stone Ltd
Lower Wharfe House,
Wharfebank Mills, Otley, Yorkshire
LS21 3JP
Tel: 01924 241 100
Email: sales@bbsnaturalstone.com
www.bbsnaturalstone.com