

ORANGE RED STOCK

CBP-CAP-DVMO-DVMA

TEXTURE, TYPE & COLOUR

Handmade facing bricks for interior and exterior use in decorative or construction walls.

Orange Red Stock from the Caprice factory; This soft mud brick has a stock & sanded texture. A combination of two special bricks. The orange and red colours blend to give a bold and distinctive look – A creative balance of colour with a crisp stock appearance.

RAW MATERIAL & PRODUCTION

The primary raw material is river clay mined in the Rhine basin - this includes floodplains and river Mass clay in the baked colours - grey-red, bright red, natural bronze and yellow.

The clay is formed in a sanded mould and fired to at least 1150 °C. The facing brick is simulated handmade or stock with frog and has a homogeneous structure. It is free from lime and other inclusions and has at least one stretcher and one header which are free from cracks and other aspects which negatively affect the overall appearance of the brickwork.


TECHNICAL CHARACTERISTICS

The facing bricks are delivered with the following characteristics, in accordance with the CE and Benor marks:

NEN-EN 771-1, April 2013, and NEN-EN 771-1/A1, March 2005 Category I, HD clay bricks.

NOTE

Dimensions may vary depending on the production. For the most recent version see www.camtechbp.co.uk. This document is not binding and annuls all previous publications. The manufacturer reserves the right to change the product range and characteristics. The user must always check that they have the most recent descriptive text.



FACTORY: CAPRICE BAKSTEEN



NEN-EN 771-1, April 2013, and NEN-EN 771-1/A1, March 2005 Category I, HD clay bricks
Production Reference code: Caprice DVMO-DVMA

Length	: 215 mm, T2 (+/- 4 mm), R1 (9 mm)
Width	: 102 mm, T2 (+/- 3 mm), R1 (6 mm)
Thickness	: 65mm, T2 (+/- 2 mm), R1 (5 mm)
Appearance	: Handmade or Stock with frog (<20% of the volume), Euro group 1
Average compressive strength	: >10 N/mm ²
Dimensional stability	: NPD
Bond strength	: Mean. 0.15 N/mm ²
Active soluble salts	: S2
Reaction to fire	: Euro class A1
Water absorption	: <16% m/md
Initial rate of water absorption	: IW4 strong suction, >4.0 kg/m ² min
Water vapour diffusion coefficient	: 5/10
Gross dry density	: 1660 kg/m ³ , D1 (10%, +/- 166 kg/m ³)
Thermal conductivity	: 0,47 W/mK
Freeze/thaw resistance	: F2

ASK FOR
SAMPLES

Call Camtech: 01763 262006



We want to help you make informed decisions and find the right solution for your business, customers or project; after all, it's much more than just a product, Right!



CAMTECH BUILDING PRODUCTS LTD
p. Camtech House, 21 Jarman Way
Royston, Herts, SG8 5HW. UK

t. +44 (0)1763 262006
e. info@camtechbp.co.uk
w. camtechbp.co.uk