

Advantages

- **Excellent thermal and acoustic insulation.**
- **Fire and temperature resistant.**
- **Chemically inert.**
- **Cost effective and easy to install.**
- **Vermin and rot proof.**
- **CFC and HFC free.**

Applications

CMS MF mineral fibre slabs are ideal for a wide range of building and industrial applications. A highly versatile material with an extensive listing of applications such as acoustic ceilings, partition panels, walls, floors, roofs, ductwork and industrial enclosures. Also, thermal insulation for boilers, heat exchangers, plant, tanks and pipes. CMS MF mineral bonded slabs can be flat or curved to suit requirements.

Description

CMS MF mineral fibre slabs are manufactured from long stranded mineral fibres that are thermo-set with resin into slabs.

Facing and Coverings

CMS MF mineral fibre slabs are available in a wide range of coverings and facings; a brief selection of coverings and facings available include:

Class 'O' foil facing.
 Glass tissue scrim 60 gm/m² (black and white).
 Glass cloth 200 gm/m² (black and white).
 Melinex polyester film.
 Ceramic paper.

Laminates

CMS MF mineral fibre slabs are also available laminated with mass barrier materials for acoustic insulation applications. Laminates include:

Polymeric mass barrier - 5, 7.5, and 10 kg/m²
 Lead sheeting - 5, 10 and 15kg/m²

Physical Information

Dimensions

Standard slab sizes are: 1200 x 600mm.
 Standard slab thicknesses are: 25, 30, 40, 50, 60, 75 and 100mm.
 Standard slab densities are: 33, 45, 60, 80, 100, 128, 140, 160 and 200 kg/m³.

Notes:

Minimum density for 25mm thick is 45kg/m³.
 Maximum thickness for 160kg/m³ is 50mm.
 Maximum thickness for 200kg/m³ is 60mm.
 Non standard slab sizes and thickness are available upon request.

Technical Information

CMS MF mineral bonded slabs conform to the following specifications:

BS 476 Part 4 - Non combustible (plain)
 BS 476 Parts 6 & 7 - Class 'O' (faced)

Resistance to compression (BS EN 826:1996)

	Density kg/m ³					
	33	60	80	100	140	200
Stress to give 10% compression (kN/m ²)	2.0	6.7	12.9	16.4	28.2	68.2
Stress to reach elastic limit (kN/m ²)	2.3	6.1	9.2	11.3	26.1	49.9
Displacement at 5kN/m ² stress (%)	38.6	7.8	3.4	2.7	1.7	0.7

Minimum Bending Radius (m)

	Slab thickness (mm)					
	30	40	50	60	75	100
Density 33 kg/m ³	0.35	0.40	0.50	0.70	0.90	1.50
Density 60 kg/m ³	0.42	0.50	0.70	1.00	1.35	1.90
Density 100 kg/m ³	0.55	0.70	1.00	1.50	2.25	2.50
Density 140 kg/m ³	1.50	1.90	2.60	3.00	3.30	3.50

Technical Information (cont)

Thermal Conductivity (W/mK) (BS 874:1973 Cold face 40°C)

Mean Temp. °C	Density kg/m ³					
	33	60	80	100	140	200
10*	0.035	0.033	0.033	0.033	0.033	0.034
50	0.043	0.039	0.038	0.037	0.037	0.034
100	0.055	0.047	0.045	0.044	0.044	0.043
150	0.070	0.058	0.055	0.054	0.051	0.050
200		0.070	0.066	0.064	0.060	0.059
250			0.079	0.075	0.070	0.068
300				0.088	0.081	0.079
350				0.104	0.093	0.089
400				0.122	0.106	0.100

* measured with a cold face temperature of 0°C

Maximum Service Temperatures

CMS MF mineral fibre slabs can be used up to a maximum temperature of 850°C, but this can vary depending on the composition of the slab / product. The phenolic resin used to bond the slabs is resistant to temperatures up to 230°C, and above this some resin will be lost to the hot surface causing discolouration.

	Service Temp. °C	Slab
Density 33 kg/m ³	175	Flexible
Density 60 kg/m ³	425	Semi rigid
Density 100 kg/m ³	525	Rigid
Density 140 kg/m ³	675	Rigid

Typical installations

CMS MF mineral bonded slab is a particularly versatile product that has a wide range of applications, typical applications include:

33 kg/m³ density slab is ideal for acoustic enclosures.

45 kg/m³ density slab is ideal for acoustic enclosures and duct lining.

60 kg/m³ density slab is ideal for acoustic enclosures, duct lining and lagging, partitions and floors.

80 kg/m³ density slab is ideal for acoustic enclosures, duct lining and lagging, partitions and floors.

100 kg/m³ density slab is ideal for duct lining, partitions and floors.

140 kg/m³ density slab is ideal for sound baffles, duct lining, partitions and floors.

200 kg/m³ density slab is ideal for sound baffles, duct lining, partitions and floors.

Acoustic Performance

CMS MF mineral fibre slabs provide excellent sound reduction characteristics by both impeding the transmission of sound and by absorption of the sound at the surface.

Absorption coefficients

Slab Density (kg/m ³)	Thickness (mm)	Frequency (Hz)					
		125	250	500	1000	2000	4000
33	40	0.10	0.45	0.82	1.00	1.00	0.82
33	50	0.10	0.60	0.90	1.00	1.00	0.88
33	60	0.22	0.75	1.00	1.00	1.00	0.94
33	75	0.24	0.53	0.89	0.94	0.96	0.83
33	100	0.39	1.00	1.00	1.00	1.00	1.00
45	25	0.05	0.25	0.55	0.75	0.90	0.81
45	40	0.14	0.40	0.87	1.00	1.00	0.82
45	50	0.25	0.65	1.05	1.10	1.05	0.96
45	75	0.50	1.05	1.20	1.15	1.10	1.13
45	100	0.80	1.15	1.20	1.15	1.15	1.16
60	25	0.10	0.20	0.65	0.85	1.00	0.68
60	40	0.13	0.49	0.95	1.00	1.00	0.86
60	50	0.25	0.65	1.05	1.10	1.10	0.98
60	75	0.55	1.10	1.20	1.15	1.15	1.15
80	25	0.06	0.25	0.55	0.88	1.00	0.67
80	40	0.11	0.61	1.00	1.00	1.00	0.90
80	50	0.16	0.72	1.00	1.00	1.00	0.93
80	60	0.25	0.90	1.00	1.00	1.00	0.98
80	75	0.39	1.00	1.00	1.00	1.00	1.00
80	100	0.89	1.00	1.00	1.00	1.00	1.00
100	25	0.05	0.30	0.76	0.95	1.05	0.75
100	40	0.12	0.44	0.88	1.00	1.00	0.95
100	50	0.35	0.85	1.10	1.10	1.15	1.05
100	75	0.44	1.00	1.00	1.00	1.00	1.00
128	50	0.40	0.90	1.00	1.00	1.00	1.00
140	50	0.40	0.90	1.15	1.05	1.10	1.05
200	50	0.40	0.50	0.70	0.70	0.70	0.65

Noise absorption is expressed as a factor between 0 and 1.0, the more sound that a surface absorbs the higher the coefficient. The composition of the MF mineral bonded fibres makes them ideal for use as sound absorbers due to the high coefficients over a wide range of frequencies.

Installation Service

In addition to supply of this product CMS Acoustic Solutions offers a competitively-priced installation service anywhere in the UK. Use of our service ensures that installation is performed to the highest standards by tradesmen fully experienced in the specialist skills of fitting acoustic materials correctly. For further details contact our technical team on 01925 577711.

E-mail: info@cmsacoustics.co.uk

Web: www.cmsacoustics.co.uk

Northern Office: 11a, Eagle Park, Eagle Park Drive, Warrington WA2 8JA
Tel: 01925 577711 Fax: 01925 577733

Southern Office: 2 Luard Way, Birch, Colchester, Essex CO2 0LR
Tel: 01206 330810 Fax: 01206 330830

IMPORTANT: Directions for use are given for guidance only and are not intended to form part of any contract. They should be varied or adapted to suit your particular materials or conditions of use. Goods supplied by the company are made to approved standards from the highest quality raw materials but no warranty or guarantee is given as to their suitability for any particular purpose or application, and no liability is accepted for any loss or damage arising directly or indirectly from the use of the Company's products irrespective of any information given to us as to intended use of such products. It is therefore recommended that prospective users should test a sample of this product under their own conditions to satisfy themselves that the product is suitable for the purpose intended.

CADS 7001 - 1 0904
© CMS Acoustic Solutions Ltd 2004