S816-300-ED Technical Data Sheet





Material: Granodiorite

Colour: Blue Grey

Source: Fujian – China

| Test | Value | BS EN |
|--|-----------|-------|
| Apparent density (g/cm ³) | 2.8 | 1936 |
| Water Absorption (%) | 0.1 | 13755 |
| Abrasion Resistance (mm) | 16.5 | 14157 |
| Flexural Strength (Mpa) LEV | 19.4 | 12372 |
| Flexural Strength (Mpa) Mean | 22.4 | 12372 |
| Flexural freeze thaw (Before/After) | 23.1/22.6 | 12371 |
| Compressive Strength (Mpa) LEV | 250 | 1926 |
| Compressive Strength (Mpa) Mean | 299 | 1926 |
| Wet Compressive Strength (Mpa) Mean | 248 | 1926 |
| Compressive freeze thaw (Before / After) | 299/290 | 12371 |
| USRV Dry (Flame Textured) | 86 | 14231 |
| USRV Wet (Flame Textured) | 58 | 14231 |
| Open Porosity (%) | 0.6 | 1936 |
| PPV (Flame Textured) | 48 | 7932 |

Maintenance

Clean warm water with natural soap would be the most common method of cleaning the stone. We also offer the Weiss range of specialist cleaning products and sealants.

Please contact our Technical Department for further information.

CED Limited - Registered No 624843 (Engand & Wales) Registered Office: 728 London Road, West Thurrock, Grays, Essex, RM20 3LU Telephone: 01708 867238 Fax: 01708 867230 Email: sales@ced.ltd.uk