

Data Sheet 12mm		Magply®	
Company information			
Manufacturer: IPP Ltd Bradwell Hall Bradwell on Sea Essex CM0 7HX Tel: 0044 (0)1621 776252, Fax: 0044 (0)1621 776688			
Board Sizes & Weights			
Board Size	Weight per board(13.19kg/m²)		
1200mm x 800mm (0.96m²)	13kg		
1200mm x 2400mm (2.88m²)	38kg		
Thermal Properties			
Thermal Conductivity (λ)	0.19 W/mK		
Thermal Resistance (R)	0.063 m²K/W		
Fire Performance			
BS EN 476 (Parts 6&7)*	Class 0		
Euroclass EN13501*	A1 (Non-Combustible)		
Physical & Chemical Properties			
Appearance:	Solid flat sheet board	Colour	White
Odour:	Odourless	Change of State:	None
Vapour Resistance	0.31 MNs/g (EN ISO 12572)		
Melting point:	2400°C	Ignitability:	N/A
Spontaneous ignition:	N/A	Explosion hazard:	N/A
Oxidising properties:	N/A	Vapour pressure:	N/A
Density	1100 g/m³	pH level:	7.5
Solubility:	Insoluble in Water	Acoustic:	Rw 29dB
Stability and Reactivity			
Special physical conditions to be avoided			
None			
Incompatible Materials			
Not known			
Hazardous Decomposition Products			
None			
Reaction to Frost			
Magply is freeze/thaw resistant			
Reaction to Moisture			
Magply is breathable and water-resistant. Passage of moisture does not affect its structure			
Reaction to Insects/Rodents			
Magply is inert and has no nutritional value, rendering it unattractive to insects and rodents.			

IPP Black Mountain

Bradwell Hall, Bradwell on Sea, Essex CM0 7HX
 Tel: 01621 776252 Fax: 01621 776688



Exposure

Magply can be left uncovered, exposed to the elements for a minimum 6 months without affecting its structure.

** for fixing detail, please refer to relevant certificate*

Fixings, Sealants, Adhesives

**Maximum loads are subject to fixing quality*

Board Thickness	Nailed picture hooks 			5mm diameter Continuous thread screw 	Toggle bolt 
9mm	20kg	18kg	5kg	20kg	40kg
12mm	25kg	23kg	10kg	25kg	45kg

Many different loads may be mounted to Magply using suitable fixings. Lightweight objects can be hung with good quality picture hooks fixed directly into the board.

Depending on the type and capacity of the method of attachment, various vertical loads can be supported by Magply. Shelves and hanging cupboards can be attached with suitable cavity fixings. The choice of attachment method will be governed by the weight and dimensions of the object.

Loads with a weight of less than 20kg per fixing point can easily be fixed to the wall with suitable screws, and 40kg using suitable toggle fixings, without the need for support noggins.

Any two points of attachment must have a minimum distance of 150mm from each other, otherwise the weight of the load to be supported must be halved. Heavy loads such as sinks, sanitary units, radiators and heavy cabinets should be fixed to the sub layer of the construction or support noggins.

When fixing Magply, screws should have a thread the whole length of the shank (to the tip) for maximum strength and resistance. Specialist details are available.

The length of fixings depends on national regulations and applications. As a guide, the fixing should be a minimum of 28mm plus the thickness of the board

For standard drywall applications, use a 12µ galvanised or phosphate coated screws or nails along with standard jointing and taping. For fire resistant applications, an intumescent sealant should be used.

When plastering and finishing, Magply should be treated as a high suction surface and any finish can be applied to either side. Please refer to and follow the plaster manufacturer's application instructions for appropriate guidance to suit your site conditions.

If required, Magply can be prepared with a nano-particle acrylic primer when being used in wet or exposed areas

**Cutting**

Magply is easily cut to size using the score and snap method using a utility knife. Mark the area out with a pencil and straight edge ensuring the reinforcing mesh is cut through. Mechanical cutting is also possible; please see Magply COSHH sheet for more details.

Liability

The information given is correct to the best of our knowledge at the time of publication but without guarantee of accuracy. We do not accept any responsibility for damage and claims arising from handling, transport, storage or disposal of the product. This data sheet applies only to the product named above supplied by IPP. If the product is used as part of other products, information given in the data sheet may be invalidated. E&OE

No warranty is hereby expressed or implied.

IPP Black Mountain

Bradwell Hall, Bradwell on Sea, Essex CM0 7HX
Tel: 01621 776252 Fax: 01621 776688