

Product Technical Information Sheet

Wienerberger Code	154915
Production Plant	Beerse (Belgium)
Manufacture	Soft Mud Moulded Stock
Configuration	Frogged
Colour	Black
Appearance	Creased
Work Size (mm)	215 x 102.5 x 65
Pack Quantity	528 No.

2.7



Technical Properties to BS EN 771-1

Individual Dry Brick Weight (kg)

Size Tolerance (Mean/Range)	T1/R1
Gross Dry Density (kg/m³/Tolerance)	1800 (D1)
Compressive Strength (N/mm²)	≥7
Thermal Conductivity (W/(m·K)) $\lambda_{10,dry,unit}$ value (EN 1745 tabulated: S1)	P=90% 0.69
Durability Designation	F2
Water Absorption (%)	≤9
Initial Rate of Water Absorption (kg/(m²·min))	Min. 1.0 Max. 5.0
Active Soluble Salts	S2
Reaction to Fire	Class A1

Issue Date: 26/05/2021

Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the Wienerberger Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.





1000+ products to choose from



Expert help and advice



Comprehensive Design Services



Technical Support